

DAY-CHEM WHITE PIGMENTED CURE-W (J-9-A)

WATER BASED – WHITE PIGMENTED

PRODUCT DESCRIPTION

A water-based, wax, liquid membrane forming curing compound for freshly finished concrete. The Day-Chem White Pigmented Cure-W (J-9-A) is white pigmented to reflect the heat of the sun.

USE

Day-Chem White Pigmented Cure-W (J-9-A) is a curing compound formulated to retain a minimum of 95% moisture in freshly finished concrete to ensure full hydration of the cement. Specifically designed for use on exterior projects such as highway pavements, residential paving, airport runways, parking lots and other pavement projects.

ADVANTAGES

- Water-based
- Meets ASTM and AASHTO Standards
- Approved by numerous state highway departments
- Clean-Up with Water
- White pigments to reflect the heat of the sun

SPECIFICATIONS

ASTM C-309 Type 2, Classes A
AASHTO M-148 Type 2, Classes A

VOC

Complies with all applicable V.O.C. standards. Actual VOC <50 g/L

APPLICATION INSTRUCTIONS

Day-Chem White Pigmented Cure-W (J-9-A) should be thoroughly stirred prior to each days use. Do not over agitate or use high speed mixing equipment. Apply immediately after all surface water has disappeared and the surface cannot be marred. DO NOT delay in applying the curing compound. Use low pressure spray, roller or brush. For best results, a spray application is the preferred method. Do not thin. Apply uniformly without puddling. Do not interchange spray equipment that has been used with solvent based curing compounds with spray equipment that has been used with water based curing compounds without thorough cleaning.

APPROXIMATE COVERAGE RATES

200 ft² per gal. (4.9m²/L)

DRY TIME

Approximately 2 hrs. at 70° F (21°C)

PACKAGING

Item#	Packaging	Size Gal./ (Liter)
69165	Pails	5 (18.9)
69164	Drums	55 (208)
69144	Tote	275 (1,040)

CLEAN-UP

Tools and Equipment Use: While wet use water. After the product dries, Dayton Superior Citrus Peel (J-48) or organic solvents such as xylene may be necessary to remove the product.

LIMITATIONS

If surface is to be painted, sealed, topped, or otherwise treated after application, surface should be checked to ensure the product has completely dissipated or removed from the substrate. Always consult with manufacturer of subsequent treatment for any additional surface preparation that may be required. Do not apply at temperature below 40°F (4°C).

Keep from freezing.

Shelf life is 12 months from date of manufacture in unopened containers.

WARNING

- Use with adequate ventilation
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, CALL A PHYSICIAN immediately. DO NOT induce vomiting

If splashed in the eyes, flush thoroughly with clean water for a minimum of 15 minutes. CALL A PHYSICIAN immediately. May cause irritation to the skin. If brought into contact with the skin, wash thoroughly with soap and water. Seek medical attention if redness or irritation occurs. Reseal container after each use. Wear protective clothing, gloves, and goggles. Read MSDS before using product.

Refer to www.daytonsuperior.com for latest Technical Data Sheet and MSDS
1125 Byers Rd., Miamisburg OH 45342
Customer Service: (888) 977-9600
Technical Assistance: (866) 329-8724

DAY-CHEM WHITE PIGMENTED CURE-W (J-9-A)

CONTINUED

MANUFACTURER

Dayton Superior Corporation
1125 Byers Rd.
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 866-329-8724
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.



Refer to www.daytonsuperior.com for
latest Technical Data Sheet and MSDS
1125 Byers Rd., Miamisburg OH 45342
Customer Service: (888) 977-9600
Technical Assistance: (866) 329-8724