



ULTRA SEAL EF

EARTH FRIENDLY, HIGH PERFORMANCE CONCRETE SEALER

PRODUCT DESCRIPTION

Ultra Seal EF is an Earth Friendly (EF) acrylic, non-yellowing concrete sealer that may contribute to LEED Credits. EF formula is low odor and contains VOC < 100 g/L, making it VOC compliant in all regions. The Ultra Seal EF is designed to seal, protect and add an attractive gloss to existing concrete and decorative concrete surfaces. Ultra Seal EF is blush resistant and has good resistance to common chemicals such as motor oil, antifreeze, vinegar and bleach.

USE

Ultra Seal EF can be used on all existing concrete and decorative concrete surfaces, where a glossy, film forming sealer is desired. Ultra Seal EF is non-yellowing making it suitable for both interior and exterior applications. This ultra low VOC sealer can be used in all VOC restricted regions in the United States.

BENEFITS

- May Contribute to LEED Credits
- Earth Friendly (EF), VOC < 100 g/L
- VOC Compliant in All Regions
- High Performance
- Resists Blushing, Hazing or Whitening
- Ultra UV Stable, Non-yellowing
- Attractive Gloss Finish
- High End Decorative Appearance
- Low Odor
- Excellent Weather ability
- High Tensile Bond Strength
- Easy Spray/Roll Application
- Non-Flammable
- Safe to Use & Store

PROPERTIES, TEST DATA

Moisture Vapor Transmission, ASTM E96:

Control, mortar disk with no coating: 45 g/24hrs.m²
Mortar disk with two coats of Ultra Seal EF: 26.8 g/24hrs.m²

Accelerated Weathering: ASTM G53: Non-Yellowing after 4000 Hours QUV

CHEMICAL RESISTANCE

Results based upon lab testing for splash, spillage and intermittent contact. Clean up all contaminants as soon as possible to avoid staining. A mock up sample is recommended to determine suitability of resistance for any particular application.

REAGENT

Ketchup
Mustard
"Kool-Aid"
Grape Juice
Coffee
Chocolate Syrup
Tincture of Iodine
Coal Tar

Stain Resistance (One Hour Exposure)

Excellent (no effect)
Excellent (no effect)
Excellent (no effect)
Excellent (no effect)
Excellent (no effect)
Excellent (no effect)
Poor
Poor

Chemical Resistance (One Hour Exposure with no Evaporation)

Used Motor Oil	Excellent (no effect)
DI Water	Excellent (no effect)
10% Sodium Hydroxide	Excellent (no effect)
10% Sodium Chloride	Excellent (no effect)
10% Calcium Chloride	Excellent (no effect)
3% Trisodium Phosphate	Excellent (no effect)
10% Ammonia	Excellent (no effect)
10% Hydrochloric Acid	Fair
Brake Fluid	Poor
100 proof alcohol	Poor
Gasoline	Poor
Skydrol	Poor

VOC

Complies with all applicable VOC standards. Actual VOC = 95g/L

MOCK UP

Provide on site mock up prior to start for approval of color, texture and workmanship.

APPLICATION

Surface Preparation

Substrates should be clean, free of all debris and contaminants and thoroughly dry. Newly placed concrete, toppings or overlays must be cured 24-48 hours from time of completed installation, depending on ambient conditions, substrate and mix design. Longer curing times are required in cool, damp conditions. Concrete curing compounds, if used must be removed prior to application of sealer. Extremely slick, dense substrates may require abrasion prior to application to achieve adequate adhesion of sealer.

Refer to www.daytonsuperior.com for latest Technical Data Sheet and MSDS
1125 Byers Road, Miamisburg OH 45342
Customer Service: (888) 977-9600
Technical Assistance: (866) 329-8724



ULTRA SEAL EF

CONTINUED

Mixing

ULTRA SEAL EF should be thoroughly mixed prior to application. Do not thin or dilute.

PLACEMENT

Apply the Ultra Seal EF by brush, roller or spray (airless spray application is recommended). Uniformly apply the Ultra Seal EF at 200 -300 ft²/gallon (4.9- 7.4 m²/L) per application. Allow the Ultra Seal EF to dry, and then uniformly apply a second coat of sealer at the same coverage rate. Ensure application is uniform and a complete film over the entire surface has been achieved. Do not apply the sealer applications too heavy or too light per coat. Light coats do not form a complete film, while heavy coats will extend the dry time and could discolor or peel. In general, two light mist coats are more effective than one heavy single coat. Re-application can take place as soon as the previous coat has dried. Protect the application from rain, snow or excessive moisture for 24 hours.

For surfaces requiring a more non-slip surface, Dayton Superior Grip Aid may be added to the Ultra Seal EF.

CLEAN UP

Clean tools, equipment and wet material with clean water. Dried material may be removed with Green Bean Clean.

WASTE DISPOSAL

Dispose of waste material and empty packaging in accordance with all Federal, State and Local requirements. Refer to the product's MSDS for further information.

ESTIMATED COVERAGE

200 - 300 ft²/gallon (4.9-7.4 m²/L) per application, 2 applications recommended.

PACKAGING

ITEM #	Package	Size	
		Gals	Liter
309454	Jug	1	3.78
309453	Pail	5	18.9
309455	Drum	55	208

STORAGE

KEEP FROM FREEZING. Store in cool dry area. Shelf life is 18 months from date of manufacture in original unopened containers.

COLOR

Milky white liquid that dries clear.

LIMITATIONS

Minimum ambient and surface temperature for application is 45°F (7.2°C) during application and for a minimum of 24 hours after application. Do not apply if rain, snow or excessive moisture is expected during application or within 24 hours after application. Do not use as a wear layer for heavy traffic areas as black tire marking and premature failure could occur.

PRECAUTIONS

Use with adequate ventilation. Keep out of the reach of children. Do not take internally. In case of ingestion, CALL A PHYSICIAN immediately. DO NOT induce vomiting. Can cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed. If eye contact occurs, flush immediately with clean water and seek medical help as needed. Read MSDS before using product.

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 866-329-8724
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.



Refer to www.daytonsuperior.com for latest Technical Data Sheet and MSDS
1125 Byers Road, Miamisburg OH 45342
Customer Service: (888) 977-9600
Technical Assistance: (866) 329-8724